

TECHNICAL DATE SHEET

ABS

Acrylonitrile-butadiene-styrene - copolymer >90%

PROPERTIES

	PROPERTIES	VALUE	METOD AND CONDICTION
PHYSICAL & MECHANICAL	Density	1,05 g/cm ³	ISO 1183/b
	Yield Stress	35 Mpa	ISO 527-1,2
	Tensile Modulus	1820 Mpa	ISO 527-1,2
	Flexural Strength	58 MPa	ISO 178
	Izod notched impact strength	23°C = 42 KJ/m ² / -30°C = 17 KJ/m ²	ISO 180-1A
THERMAL	Heat deflection temperature	97 °C	ISO 75
	Burning behavior	HB	UL 94

SUGGESTED PRINTER SETTING

	VALUE	UNIT
Extruder Temperature	250 - 290	°C
Print Speed	30 - 60	mm/s
Printbed temperature	80 -100	°C
Drying Temperature	80 - 90	°C for 2-4 hr

PRODUCT DETAILS & CERTIFICATION

Diameter	1,75 mm 2,85 mm	Tolerance ± 0,05mm Tolerance ± 0,05mm
Major Benefits	<ul style="list-style-type: none"> - Super high impact - Polishable - Resistant to low temperature - Good printability and resolution - Post processable 	

The information supplied in relation to our products recommendations or otherwise, is collected from source considered to be dependable or internally developed. Ciceri de Mondel Srl assumes no liability and makes no warranties of any kind about the accuracy of this datas. The user assumes all responsibility for the use of all information provided and shall.